

K A U F M A N

PRODUCT
INFORMATION

**KAUFMAN
PRODUCTS
INC.**

3811 CURTIS
AVENUE

BALTIMORE,
MARYLAND
21226-1131

410-354-8600
800-637-6372
[www.kaufman
products.net](http://www.kaufmanproducts.net)

DressUp

Description

DressUp is the original cementitious finishing compound for concrete. It contains special Portland cements, properly graded and sized quartz aggregates, and unique plasticizing agents. The compound, when uniformly blended, unites to mesh perfectly into a dense, water repellent, uniform finishing agent for concrete and masonry walls. DressUp produces a strong, highly adherent surface that actually becomes part of the wall itself to provide a lifetime of beauty, protection and water repellence. It will not peel or crack like a coating and it possesses good breathing characteristics.

Uses

DressUp eliminates rubbing concrete walls, columns and underside of slabs. Anytime after forms are stripped, DressUp may be brushed or troweled on the concrete and floated to provide uniformly colored and even textured surfaces. Air voids, pores, honeycombs, joints, tie-holes, form marks and other blemishes inherent in monolithic concrete work, are completely filled and sealed making the surface uniform in color and texture. No more straining of sands and blending with cement which produces uneven colors. Even un-filled form joint depressions are the same color as the surrounding surface. It has the unusual feature of being uniform in color even with uneven application thickness.

Physical Properties @ 75°F

		Dress Up	Field Mixes
Comp. strength, psi.	1 day	1200	1200
	7 days	3700	4470
	28 days	6400	4470
	28 days	3500	50
ASTM C-882			
Tensile strength, psi.	1 day	310	110
	7 days	350	150
	28 days	535	235
Flexural strength, psi.	1 day	-	-
	7 days	1015	420
	28 days	1120	610
Abrasion Resistance (% wgt. lost of dry sample)	1.92	21.7	

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY We warrant our products to be of good quality and will replace material proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement, Kaufman Products, Inc makes no warranty or guarantee, expressed or implied, including warranties of fitness or merchantability, respecting its products, and Kaufman Products, Inc shall have no other liability with respect hereto. User shall determine the suitability of the product or the intended use and assume all risks and liability in connection thereto. Our salesmen, distributors and their salesmen have no authority to change the printed recommendations concerning the use of our products.

Color

Natural

Coverage

Per Kit:

1/16" thick - 80 sq. ft.

1/32" thick - 160 sq. ft.

Per Bag:

1/16" thick - 100 sq. ft.

1/32" thick - 200 sq. ft.

VOC

0 grams/liter

Directions**Surface Preparation**

Surfaces to be coated must be structurally sound, clean and free of foreign matter, protective coating, laitance, efflorescence, form oil, etc. Cut tie rods to a depth of one half inch and patch all holes, large cracks and honeycomb areas.

Mixing

Mix the entire contents of both components (or proportional amounts of each by volume) until uniformly blended. Either potable water, or our latex additive, SureBond, may be used. Water repellency, wearability and strengths are increased with the use of SureBond. Hand mixing with trowel, scoop or hoe is satisfactory, making sure that all pockets of dry material are thoroughly blended into the wetted mass. If mechanical mixing is preferred use a slow speed heavy-duty ½" drill with paddle blade or mortar mixer. Always be sure to add the liquid to the powder.

Application

If surface is hot, cool by hosing wall before application. Do not apply when temperature is 40°F or below, or expected to drop below 40°F within 24 hours. Knock off any large projection before application. It is recommended that all walls be wetted before DressUp is applied. Apply with float or white wash brush. Lightly trowel or float with sponge or cork to a smooth surface. Do not steel trowel smooth or burnishing marks will appear. (Special effects can be obtained by using burlap to rub walls.) Faster type spray units can also be used to speed work and achieve a slightly coarse texture.

Packaging

5 gallon heavy-duty pail with handle, containing 40 lbs. fine powder and 1 gallon jug of liquid bonding emulsion. Gross weight per kit - 50 lbs.

50 lb. bag of Cementitious blend to be used in conjunction with 1 gallon of SureBond.

Precautions

DressUp is only intended for concrete and masonry wall surfaces. All surfaces should be clean, free of dirt, laitance, grease, loose mortar and form oil. If adhesion is in doubt, it is always a good idea to try to test patch first. Protect from freezing. Do not use below 40°F, or if temperature is expected to drop to that point within 24 hours after application. Do not steel trowel smooth, as gray burnishing marks will appear. Do not use curing compounds. Read Material Safety Data before using.

F:\T\Eng. Literature with Heading\030.doc